

ชื่อเรื่อง การแยกโพทัลส์เชี่ยมคลอไรด์จากการน้ำแล้วโดยใช้ตัวทำละลาย  
โพร์ติก

ชื่อผู้เขียน นางสุมาลี สุบงกช  
การศนควาแบบอิสระ เชิงวิทยานิพนธ์ วิทยาศาสตร์มหาบัณฑิต สาขาวิชาการสอนเคมี  
มหาวิทยาลัยเรียงใหม่ 2526

บทคัดย่อ

ได้ศึกษาวิธีแยกโพทัลส์เชี่ยมคลอไรด์ออกจากสารน้ำแล้วโดยใช้ตัวทำละลายโพร์ติกซึ่งในที่นี้ใช้สารละลายมักน้ำเชี่ยมคลอไรด์ในน้ำเข้มข้น 20 % และ 25 % โดยนำหนักตอน้ำหนักเป็นตัวทำละลาย ละลายสารน้ำแล้วในตัวทำละลายจนอิ่มตัวและต้มให้น้ำระเหยไปจนเป็นของเหลวข้น กรองเอ้าท์เตอร์ เก็บออกและสลายคั่วยนำจำนวนพอเหมาะสม และกรองอีกครั้งหนึ่ง จะได้คลีวิไนท์สังเคราะห์ ( $\text{NaCl}\cdot\text{KCl}$ ) เอาไปล้างด้วยน้ำแล้วนำไปจ่ายในสารละลายนิวเคลียร์ซึ่งเป็นส่วนผสมของโซเดียมคลอไรด์และโพทัลส์เชี่ยมคลอไรด์ ปรับให้โซเดียมคลอไรด์และโพทัลส์เชี่ยมคลอไรด์ในสารละลายนี้อัตราส่วนเป็น 1:1 โดยนำหนักและต้มที่ 100 องศาเซลเซียส พอเริ่มอิ่มตัวโซเดียมคลอไรด์จะแตกตะกอน กรองออกขณะแล้วทำการให้ถูกเทรทเย็นถึง 0 องศาเซลเซียส โพทัลส์เชี่ยมคลอไรด์จะตกผลึกออกมาก ผลการทดลองเมื่อใช้ตัวทำละลายเข้มข้น 20 % และ 25 % กับการน้ำแล้วโดยตัวอย่างที่ 1 ซึ่งมีโพทัลส์เชี่ยม 11.25 % จะแยกโพทัลส์เชี่ยมคลอไรด์ได้ 38 % และ 51 % และบริสุทธิ์ 95 % และ 97 % ตามลำดับ เมื่อใช้การน้ำแล้วโดยตัวอย่างที่ 2 ซึ่งมีโพทัลส์เชี่ยม 9.62 % กับตัวทำละลายเข้มข้น 25 % จะ

แยกไปตั้งเชี่ยมกลอไรก็อกมาได้ 38 % และบริสุทธิ์ 93 % โค้ทกองใช้โคมาร์ต  
กราฟฟิคแลกเปลี่ยนอ่อน แยกไปตั้งเชี่ยมกลอไรก็อกจากชีลวีไนท์ ปรากฏว่าแยก  
ไปตั้งเชี่ยมกลอไรก็อกมาได้ 87.69 % และบริสุทธิ์ 97.43 %



อิชสิทธิ์มหาวิทยาลัยเชียงใหม่  
Copyright © by Chiang Mai University  
All rights reserved

Research Title Separation of Potassium Chloride from Carnallite  
by Protic Solvents

Name Ms.Sumalee Subongkot

Research For Master of Science in Teaching Chemistry  
Chiang Mai University 1983

Abstract

A separation method of potassium chloride from carnallite by a protic solvent was studied. Aqueous solution of magnesium chloride of 20 % and 25 % W/W were used as a solvent. Carnallite was dissolved in aqueous solution of magnesium chloride to give a saturated solution, then the solution was boiled to be slurry and filtered. The filter cake was decomposed with sufficient water and it was filtered to yield synthetic sylvite ( $\text{NaCl} \cdot \text{KCl}$ ). The synthetic sylvite was dissolved in nucleus solution which contains sodium chloride and potassium chloride. The resulting solution was adjusted to contain  $\text{NaCl}$  and  $\text{KCl}$  in the ratio of 1:1 W/W and boiled at  $100^\circ\text{C}$ . When the solution was saturated, sodium chloride would be precipitated and it was filtered. The potassium chloride in filtrate would be crystallized at  $0^\circ\text{C}$ . According to this process, carnallite 1 which contains 11.25 % K

was dissolved in 20 % and 25 % aqueous solution of magnesium chloride. The yield of potassium chloride were 38 % and 51 % with the purity of 95 % and 97 % respectively. Carmallite 2 containing 9.62 % K was dissolved in 25 % magnesium chloride aqueous solution. The yield of potassium chloride was 38 % and 93 % pure. Ion exchange chromatography was also used to separate potassium chloride from synthetic sylvinite. The yield of potassium chloride was 87.69 % and 97.43 % pure.