

**Thesis Title** The Structure-Property Relationships Involved in the  
In Vitro Biodegradation of Some Speciality Biomedical  
Polymers

**Author** Miss Montira Sriyai

**M.S.** Chemistry

**Examining Committee :**

Dr. Nipapan Molloy	Chairman
Dr. Robert Molloy	Member
Dr. Tiwaporn Siri Wittayakorn	Member

## ABSTRACT

The biodegradable polyesters of particular interest in this work, poly(glycolic acid) (PGA), poly( $\delta$ -valerolactone) and poly(glycolic acid-co-valerolactone) (P(GA-co-VL)), were synthesized via stannous octoate-initiated ring-opening polymerizations. The polymers obtained were characterized according to their chemical structure and composition (IR, C-13 NMR spectroscopy and elemental CHNS/O analysis), molecular weight (vapour pressure osmometry, dilute-solution viscometry) and thermal properties (DSC, TG). From the results obtained, the P(GA-co-VL) copolymer products contained much less valerolactone than in their initial comonomer feeds because glycolide was much more reactive than  $\delta$ -valerolactone. For example, an initial comonomer feed containing 50% by mole VL gave a copolymer which contained only about 10% by mole VL. The molecular weights obtained were also low, in the range of  $\bar{M}_n = 1000-5000$ , a factor of 10 less than the target value. In vitro biodegradability studies of the PVL and P(GA-co-VL) copolymers were conducted in a phosphate buffer medium of pH 7.40 and temperature of  $37.0 \pm 0.1^\circ\text{C}$ . Samples were prepared in the form of monofilament fibres by a melt spinning process. Property changes in weight, melting point, heat of fusion and intrinsic viscosity were determined at weekly intervals over a total immersion period of 24 weeks. Based on the results obtained, a mechanism

for the in vitro biodegradation could be described in terms of the physical and chemical processes taking place. Differences between the property-loss profiles of PVL and P(GA-co-VL) were interpreted in terms of the differences in their chemical structures and, in some instances, physical configurations.

มหาวิทยาลัยเชียงใหม่  
Chiang Mai University

**ชื่อเรื่องวิทยานิพนธ์**      ความสัมพันธ์ระหว่างโครงสร้างและสมบัติที่เกี่ยวข้อง  
ในการสลายตัวทางชีวภาพ อิน วิโทซ ของไบโอเมดิกัล  
พอลิเมอร์เฉพาะอย่างบางตัว

**ชื่อผู้เขียน**                      นางสาว มณธิรา ศรีไย

**วิทยาศาสตร์มหาบัณฑิต**    สาขาวิชาเคมี

**คณะกรรมการสอบวิทยานิพนธ์**      :

ดร. นิภาพันท์ มอลลอย                      ประธานกรรมการ

ดร. โรเบิร์ต มอลลอย                      กรรมการ

ดร. ทิวพร ศิริวิทยากร                      กรรมการ

## บทคัดย่อ

ในงานวิจัยนี้มีการสังเคราะห์พอลิเอสเทอร์ที่สามารถสลายตัวได้ทางชีวภาพที่สนใจ คือ พอลิไกลคอลลิก แอซิด (พีจีเอ) พอลิ(เดลต้า-วาลอโรแลคโตน) และ พอลิ(ไกลคอลลิก แอซิด-โค-วาลอโรแลคโตน) (พีจีเอ-โค-วีแอล) โดยการพอลิเมอไรเซชันแบบเปิดวง โดยใช้สแตนเนส ออกโทเอท เป็นตัวเริ่มปฏิกิริยา พอลิเมอร์ที่สังเคราะห์ได้มีการหา ลักษณะเฉพาะตามโครงสร้างทางเคมีและองค์ประกอบ (ไออาร์ คาร์บอน-13 เอ็นเอ็มอาร์ สเปกโตรสโคปี และ การวิเคราะห์ปริมาณธาตุโดยการวิเคราะห์คาร์บอน ไฮโดรเจน ไนโตรเจน/ออกซิเจน) น้ำหนักโมเลกุล (การวัดความดันออสโมติก และ การหาความหนืดของสารละลายเจือจาง) และ สมบัติทางความร้อน (ดีเอสซี และ ทีจี) ผลที่ได้พบว่า พีจีเอ-โค-วีแอลโคพอลิเมอร์ มีองค์ประกอบของวาลอโรแลคโตนต่ำกว่าใน โมโนเมอร์

ผสมเริ่มต้นเนื่องจากไกลโคไลด์มีความว่องไวในการทำปฏิกิริยาสูงกว่าเซลล์ตัว  
วาลอโรแลคโตนอย่างมาก ตัวอย่างเช่น เมื่อใช้โมโนเมอร์ผสมเริ่มต้นที่มีวีแอล 50%  
โดยโมล จะให้โคพอลิเมอร์ที่ประกอบด้วย วีแอลเพียง 10% โดยโมล น้ำหนักโมเลกุล  
ที่ได้มีค่าต่ำอยู่ในช่วงของ  $\bar{M}_n$  เท่ากับ 1000-5000 ซึ่งต่ำกว่าเป้าหมาย 10 เท่า  
การศึกษาการสลายตัวทางชีวภาพแบบ อิน วิโทร ของ พีวีแอล และ พี(จีเอ-โค-วีแอล)  
โคพอลิเมอร์ ทำในสารละลายฟอสเฟตบัฟเฟอร์พีเอช 7.40 และ อุณหภูมิ  $37 \pm 1^\circ\text{C}$   
การเตรียมสารตัวอย่างทำในรูปของเส้นใยโพลิเอทิลีนจากกระบวนการปั่นแบบหลอม  
เหลวมีการหาสมบัติที่เปลี่ยนแปลงในน้ำหนัก จุดหลอมเหลวความร้อนของการหลอมเหลว  
และ ความหนืดอินทรีนซิก ทุกสัปดาห์เป็นเวลา 24 สัปดาห์ จากผลที่ได้สามารถ  
นำมาอธิบายกลไกการสลายตัวทางชีวภาพแบบ อิน วิโทร ในรูปของกระบวนการ  
การต่างๆทางกายภาพและทางเคมีที่เกิดขึ้น สามารถอธิบายความแตกต่างของลักษณะ  
การสูญเสียสมบัติของพีวีแอล และ พี(จีเอ-โค-วีแอล) ได้ในรูปของความแตกต่างของ  
โครงสร้างเคมีและ การจัดเรียงตัวทางกายภาพ