

<b>Thesis Title</b>	Spectroscopy of Thai Corundum
<b>Author</b>	Mr. Yongyoot Khunkaew
<b>Degree</b>	Master of Science (Geology)
<b>Thesis Advisor</b>	Assoc. Prof. Dr. Theerapongs Thanasuthipitak

### ABSTRACT

Thai corundum deposits are located in Chanthaburi-Trat, Kanchanaburi, Phrae-Sukhothai, Ubon Ratchathani-Si Sa Ket, and Phetchabun provinces. The most productive are those deposits in Chanthaburi-Trat and Kanchanaburi. The deposits in Chanthaburi-Trat and Ubon Ratchathani-Si Sa Ket produce both ruby and sapphire while others produce only sapphire.

More than 100 corundum samples from these deposits were studied using basic gemological instruments and spectroscopic techniques (UV/VIS/NIR, FTIR, Raman, and ED-XRF) to determine characteristic spectra, the relationship between spectrum patterns and chemical composition, as well as causes of the spectral line.

The characteristic features of Thai corundums, such as fluorescence, mineral inclusions, trace element contents, and spectroscopy, are comparable to other documented corundums associated with basalt, and can be used to distinguish from metamorphic corundums.

Most Thai ruby samples are purplish red with UV/VIS/NIR absorption spectra showing a combination absorption of red, due to  $\text{Cr}^{3+}$  *d-d* transition at 555, 410 and 693 nm, and blue, due to  $\text{Fe}^{2+}/\text{Ti}^{4+}$  IVCT between 550 and 700 nm, and  $\text{Fe}^{3+}$  *d-d* transition at 376, 388 and 450 nm. Correspondingly the Fe and Ti contents are quite

high: averaging more than 0.70 wt.%  $\text{Fe}_2\text{O}_3$  and  $> 0.05$  wt.%  $\text{TiO}_2$ , when compared with metamorphic rubies.

All Thai blue sapphire samples exhibit low intensity absorption spectra of the crystal field transition ( $d-d$ ) for  $\text{Fe}^{3+}$  at 376, 388 and 450 nm, and high intensity broad absorption band of  $\text{Fe}^{2+}/\text{Ti}^{4+}$  intervalence charge transfer between 550 and 700 nm. They also show  $\text{Fe}^{2+}/\text{Fe}^{3+}$  intervalence charge transfer absorption band between 870 and 890 nm that are related to the absorption peak of OH in mid-infrared range at  $3309\text{ cm}^{-1}$  due to charge compensation process. The trace element contents show higher  $\text{Fe}_2\text{O}_3$  (0.5-1.7 wt.%) and  $\text{TiO}_2$  (0.03-0.1 wt.%) than most metamorphic blue sapphires.

The intensity of corundum's absorption bands is most influenced by the molar absorption coefficient ( $\epsilon$ ), which is, in turn, governed by electron transition selection rule. The difference in spectrum patterns of the o-ray and e-ray directions is related to IVCT transition, and the  $\epsilon$  values involved in this instance, are governed by the corundum crystal structure.

ลิขสิทธิ์มหาวิทยาลัยเชียงใหม่

Copyright© by Chiang Mai University

All rights reserved

ชื่อเรื่องวิทยานิพนธ์

สเปกโทรสโกปีของคอร์นคัมจากประเทศไทย

ผู้เขียน

นายยงยุทธ ชันแก้ว

ปริญญา

วิทยาศาสตร์มหาบัณฑิต (ธรณีวิทยา)

อาจารย์ที่ปรึกษาวิทยานิพนธ์

รศ. ดร. ชีรพงศ์ ธนสุทธิพิทักษ์

### บทคัดย่อ

แหล่งคอร์นคัมของประเทศไทยพบที่จังหวัด จันทบุรี-ตราด, กาญจนบุรี, แพร่-สุโขทัย, อุบลราชธานี-ศรีสะเกษ และเพชรบูรณ์ แหล่งผลิตที่สำคัญ คือ จันทบุรี-ตราด และ กาญจนบุรี โดยแหล่งจันทบุรี-ตราด และ อุบลราชธานี-ศรีสะเกษ มีทั้งทับทิมและแซปไฟร์ ในขณะที่แหล่งอื่นพบเฉพาะแซปไฟร์เท่านั้น

คอร์นคัมกว่าร้อยละ ๖๐ จากแหล่งเหล่านี้นำมาศึกษาโดยเครื่องมือพื้นฐานทางอัญมณีและเทคนิคทางสเปกโทรสโกปี เช่น ยูวี/วิสิเบิล/เนียร์อินฟราเรด, ฟลูออโรสโคปอินฟราเรด, รามานสเปกโทรสโกปี และเอนเนอซีคิสเพอสิฟอริกซ์เรย์ฟลูออเรสเซนส์ เพื่อกำหนดลักษณะเฉพาะของสเปกตรัม และหาความสัมพันธ์ระหว่างรูปแบบสเปกตรัมกับธาตุองค์ประกอบ พร้อมทั้งสาเหตุการเกิดเส้นสเปกตรัม

ลักษณะเฉพาะของคอร์นคัมในการศึกษาครั้งนี้ เช่น การเรืองแสง, แร่มลทิน, ปริมาณธาตุร่องรอย และสเปกโทรสโกปี มีลักษณะคล้ายกับคอร์นคัมแหล่งอื่นที่สัมพันธ์กับหินบะซอลต์ และสามารถชี้แยกจากคอร์นคัมที่สัมพันธ์กับหินแปรได้

ตัวอย่างทับทิมไทยส่วนใหญ่มีสีแดงอมม่วง แสดงการดูดกลืนแสงที่เป็นผลรวมระหว่างสเปกตรัมของสีแดง ซึ่งเกิดจากการย้ายอิเล็กตรอนภายในอ็อกซิดของธาตุโครเมียม แสดงสเปกตรัมที่ตำแหน่ง 555, 410 และ 693 นาโนเมตร และสเปกตรัมสีน้ำเงินซึ่งเกิดจากการถ่ายเทประจุระหว่างเฟอร์รัสอ็อกไซด์และไทเทเนียมอ็อกไซด์ในช่วง 500 – 700 นาโนเมตร และการย้ายอิเล็กตรอนภายในเฟอร์ริกอ็อกไซด์ แสดงสเปกตรัมที่ตำแหน่ง 376, 388 และ 450 นาโนเมตร ทำให้ทับทิมไทยมีปริมาณ

เหล็กและไทเทเนียมก่อนข้างสูง กล่าวคือ เหล็กออกไซด์ เหล็กละเอียดมากกว่า 0.70 เปอร์เซ็นต์โดยน้ำหนัก และไทเทเนียมออกไซด์ เหล็กละเอียดสูงกว่า 0.05 เปอร์เซ็นต์โดยน้ำหนัก เมื่อเทียบกับทับทิมที่เกิดในแหล่งหินแปร

ตัวอย่างไพลินทั้งหมดจากประเทศไทยแสดงการดูดกลืนแสงที่ความยาวคลื่นที่ตำแหน่ง 376, 388 และ 450 นาโนเมตรซึ่งมีความเข้มต่ำเกิดจากการย้ายอิเล็กตรอนภายในเฟอร์ริกอิออน ร่วมกับการถ่ายประจุระหว่างเฟอร์ริอิออนและไทเทเนียมอิออนในช่วง 500 - 700 นาโนเมตรซึ่งมีความเข้มสูง และการถ่ายประจุระหว่างเฟอร์ริอิออนและเฟอร์ริกอิออนในช่วง 870 - 890 นาโนเมตร โดยมีความสัมพันธ์กับการดูดกลืนแสงเลขคลื่นที่ตำแหน่ง 3309 ของพันธะไฮดรอกไซด์ ซึ่งเกิดจากกระบวนการชดเชยประจุ และไพลินไทยมีปริมาณธาตุร่องรอยของเหล็กออกไซด์ (0.5 - 1.7 เปอร์เซ็นต์โดยน้ำหนัก) และไทเทเนียมออกไซด์ (0.03 - 0.1 เปอร์เซ็นต์โดยน้ำหนัก) สูงกว่าไพลินส่วนใหญ่ที่เกิดในแหล่งหินแปร

ความเข้มของแถบดูดกลืนแสงของคอร์ันดัม ขึ้นอยู่กับค่าสัมประสิทธิ์ดูดกลืน โมลาร์ ( $\epsilon$ ) เป็นสำคัญ ซึ่งจะมีค่าเป็นไปตามกฎการเลือกที่จะยอมให้เคลื่อนย้ายอิเล็กตรอนหรือไม่ ส่วนความแตกต่างของสเปกตรัมที่วัดตามทิศทางตั้งฉากหรือขนานกับแกนแสงของผลึกคอร์ันดัมจะเกิดกับกระบวนการถ่ายประจุระหว่างอิออนเท่านั้น โดยที่ค่า  $\epsilon$  ในกรณีนี้ขึ้นอยู่กับทิศทางตามโครงสร้างผลึกคอร์ันดัม