

ชื่อเรื่องวิทยานิพนธ์

การแยกสลายของพอลิสไตรีนด้วยความร้อน

ผู้เขียน

นายกฤดาชัย รัมพล

ปริญญา

วิทยาศาสตรมหาบัณฑิต (เคมีอุตสาหกรรม)

อาจารย์ที่ปรึกษาวิทยานิพนธ์

อาจารย์ ดร. จันทรารณ พุ่มชูศักดิ์

บทคัดย่อ

ได้มีการศึกษาหาสภาวะที่เหมาะสมในการแยกสลายด้วยความร้อนของเม็ดพลาสติกพอลิสไตรีนและขยะพลาสติกพอลิสไตรีน โดยใช้เตาปฏิกรณ์แบบเบ肯นิงขนาดสำหรับห้องปฏิบัติการที่ออกแบบและสร้างขึ้นมา อุณหภูมิที่ใช้ในการแยกสลายนี้เท่ากับ 450, 500, 600 และ 700°C และอัตราการไหลดของก้าชในโตรเจนเท่ากับ 50, 100, 200 และ 300 มล./นาที พบว่าในหนักพลาสติกที่เหมาะสมสำหรับเตาปฏิกรณ์คือ 30 กรัม โดยในการแยกสลายเม็ดพลาสติกที่อุณหภูมิ 500°C จะให้สไตรีนอนออกมากที่สุดและที่ $600, 450$ และ 700°C จะให้สไตรีนนอนออกมากตามลำดับ การทดลองนี้ได้ปริมาณสไตรีนนอนออกมากที่สุดคือ 52.10 เปอร์เซ็นต์โดยน้ำหนัก ที่อุณหภูมิการแยกสลาย 500°C อัตราการไหลดของก้าชในโตรเจนเท่ากับ 200 มล./นาที สำหรับการแยกสลายของพลาสติกพอลิสไตรีนพบว่าที่อุณหภูมิ 500°C อัตราการไหลดของก้าชในโตรเจนเท่ากับ 100 มล./นาที จะให้ปริมาณสไตรีนนอนออกมากที่สุดคือ 45.04 เปอร์เซ็นต์โดยน้ำหนัก

Copyright by Chiang Mai University
All rights reserved

Thesis Title

Pyrolysis of Polystyrene Waste

Author

Mr. Kridatun Rompol

Degree

Master of Science (Industrial Chemistry)

Thesis Advisor

Dr. Jantrawan Pumchusak

Abstract

Optimum pyrolysis condition of polystyrene pellets and polystyrene wastes by a home designed and built laboratory fixed-bed reactor was determined. The reactor temperatures were 450, 500, 600 and 700°C with nitrogen as the carrier gas at flow rates of 50, 100, 200 and 300 ml/min. It was found that the suitable amount of plastic for this reactor was 30 grams. The pyrolysis of polystyrene pellets at 500°C gave the highest styrene monomer yield, the lower yields were obtained at the reactor temperatures of 600, 450 and 700°C respectively. This study gained the maximum yield of styrene monomer at 52.10 wt.% at a pyrolysis temperature of 500°C and nitrogen flow rate of 200 ml/min. For polystyrene wastes, it was found that at 500°C and nitrogen flow rate of 100 ml/min would give a maximum yield of styrene monomer at 45.04 wt.%.