


จากการบ่มด้วยวิธีไฮโดรเทอร์มอล เมื่อเพิ่มปริมาณแคลเซียมไฮดรอกไซด์ หรืออัตราส่วนแคลเซียมต่อซิลิกา พบว่าจะให้ค่าการทนต่อแรงกดอัดอยู่ในช่วง 13.6 – 20.9 MPa สำหรับการใส่แคลเซียมคาร์บอเนตเป็นสารให้ความเป็นเบส เมื่ออัตราส่วนแคลเซียมต่อซิลิกาเพิ่มขึ้น ส่งผลให้ค่าการทนต่อแรงกดอัดเพิ่มขึ้นด้วย อยู่ในช่วง 5.9 – 6.3 MPa และจากองค์ประกอบทางแร่ที่ตรวจพบด้วย XRD พบสารประกอบใหม่ที่เกิดขึ้นจากปฏิกิริยาพอซโซลานิก คือ แอนดราไต์ แคลเซียมซิลิเกต และแอลไบต์แคลไซต์ จากโครงสร้างทางจุลภาคปรากฏผลึกคล้ายกับตาข่ายซึ่งจะเกิดอยู่ในรูปของแอนดราไต์ และลักษณะผลึกกลุ่มก้อนสีขาวจากการ EDS พบว่าน่าจะเป็นองค์ประกอบของผลึก C-S-H และพบว่าเมื่ออัตราส่วนของ CaO/SiO₂ เพิ่มขึ้นส่งผลให้ผลึกของ C-S-H ลดน้อยลง และจากเทคนิค FTIR และ DTA&TGA สามารถบ่งบอกถึงการมีอยู่ของ C-S-H ถึงแม้ว่าเทคนิค XRD ไม่สามารถตรวจพบได้ก็ตาม เมื่อใช้ CaO/SiO₂ เท่ากับ 1 และกระตุ้นด้วยการใช้โซเดียมไฮดรอกไซด์ โปแทสเซียมไฮดรอกไซด์ และสารประกอบซัลเฟต พบว่าการกระตุ้นด้วยโซเดียมไฮดรอกไซด์ จะมีค่าการทนต่อแรงกดอัดในช่วง 13.8 – 35.8 MPa และที่ความเข้มข้น 5 โมลลาร์ของโซเดียมไฮดรอกไซด์ จะให้ค่าความแข็งแรงสูงสุด สำหรับการใส่โพแทสเซียมไฮดรอกไซด์เป็นตัวกระตุ้น มีผลให้ค่าการทนต่อแรงกดอัดอยู่ในช่วง 15.3 – 22.6 MPa และที่ความเข้มข้น 5 โมลลาร์ของโพแทสเซียมไฮดรอกไซด์ จะให้ค่าความแข็งแรงสูงสุด และเมื่อใช้สารประกอบซัลเฟต พบว่าให้ค่าการทนต่อแรงกดอัดอยู่ในช่วง 12.5 – 15.7 MPa โดยค่าที่มากที่สุดอยู่ที่การกระตุ้นด้วยสารประกอบซัลเฟต จากเอฟฟิซีฟิซมร้อยละ 5 โดยน้ำหนัก และพบว่าการกระตุ้นด้วยโซเดียมไฮดรอกไซด์ จะส่งผลให้เจ้าหน้าที่มีสภาพไวต่อปฏิกิริยาพอซโซลานิกได้มากที่สุด และการเติมสารประกอบซัลเฟตไม่ได้ส่งผลให้เกิดสภาพไวปฏิกิริยาพอซโซลานิกได้เพิ่มขึ้น ที่สภาวะการบ่มภายใต้ความชื้นที่อุณหภูมิ 70 องศาเซลเซียส ให้ค่าการทนต่อแรงกดอัดอยู่ในช่วง 10.0 – 13.7 MPa จากองค์ประกอบทางแร่พบสารประกอบใหม่คือ แอลไบต์แคลไซต์ และจากโครงสร้างทางจุลภาคพบผลึกของ C-S-H ได้เช่นกัน อิฐ-โลม ที่ภายใต้สภาวะความชื้นที่อุณหภูมิห้องเป็นเวลา 28 วัน จะให้ค่าการทนต่อแรงกดอัดอยู่ในช่วง 11.8 – 19.2 MPa โดยมีค่าความแข็งแรงใกล้เคียงกันกับอิฐที่บ่มในหม้ออัดความดัน จากองค์ประกอบทางแร่ และโครงสร้างทางจุลภาคจะพบเหมือนกับการบ่มด้วยวิธีไฮโดรเทอร์มอล การบ่มด้วยวิธีไฮโดรเทอร์มอลทำให้สภาพไวปฏิกิริยาพอซโซลานิกเพิ่มขึ้นได้

Thesis Title	Pozzolanic Reactivity of Bottom Ash from the Mae Moh Power Plant
Author	Mr. Thawatchai Iamsin
Degree	Master of Science (Industrial Chemistry)
Thesis Advisor	Asst. Prof. Dr. Kedsarin Pimraksa

Abstract

This research studied the pozzolanic reactivity of bottom ash from Mae Moh Power Plant. Pozzolanic reaction takes place when silica, alumina and iron contained bottom ash dissolved, react with calcium ions resulting in binding materials such as calcium silicate hydrate (C-S-H). $\text{Ca}(\text{OH})_2$ and CaCO_3 (from wood ash) were used as pozzolanic reaction inducers to produce solidified bricks in this study. Various factors viz. Lime contents (CaO/SiO_2 ratio), curing methods and activation additives affecting to mechanical properties, mineralogical compositions and microstructures of unfired bricks were studied. The ratios of CaO/SiO_2 (Ca/Si) were varied as 1.0, 2.0 and 4.0, and 1.0, 2.0 and 3.0 when $\text{Ca}(\text{OH})_2$ and wood ash were used, respectively. Hydrothermal process at 130 ± 5 °C (0.14 MPa of pressure), oven curing method at 70 and 100 °C under moist atmosphere and cured in moist ambient temperature at 28 and 90 days was used to cure green lime bricks. Sulfate compound from FGD-gypsum was used to activate the dissolution stage of alumina contained bottom ash. NaOH and KOH were also used to activate a pozzolanic reactivity. Compressive strength value and C-S-H phase development are used to indicate the pozzolanic reactivity. Lime bricks were shaped into rectangular bar with dimension of $6 \times 10 \times 4 \text{ cm}^3$ with water to solid ratio of 0.25. The autoclaved $\text{Ca}(\text{OH})_2$ bricks with an increase in calcium hydroxide content or Ca/Si ratio result in a decrease in mechanical strength. The value of compressive strength was in the range of 13.6-20.9 MPa. An increase in Ca/Si ratio enhanced the mechanical strength for autoclaved CaCO_3 bricks. New phases developed after the pozzolanic reaction were andradite, calcium silicate and albite-calcite confirmed by XRD. The morphology of the new phases were net-like particles in the form of andradite phase and white bulky solid in the form of C-S-H, analyzed by EDS. An increase in CaO/SiO_2 ratio decreased the crystallized particle amount of C-S-H. FTIR and DTA&TGA analysis can detect the existence of C-S-H which could not be detected by XRD. Using NaOH activation with a Ca/Si of 1, the compressive strength of the autoclaved brick was in the range of 13.8-35.8 MPa. The highest compressive strength was obtained at 5 M NaOH activation. For KOH, an increase in the concentration enhanced the strength which was in the range of 15.3-22.6 MPa. The maximum value of strength was obtained at 5 M KOH activation. The autoclaved bricks with sulfate compound activation gave the compressive strength in the range of

12.5-15.7 MPa. Addition of 5 wt% FGD-gypsum ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$) results in the highest compressive strength among the sulfate activated lime bricks. Sulphate compound addition could not increase the pozzolanic reactivity. Curing in moist oven at 70 °C gave the compressive strength in the range of 10.0-13.7 MPa. New phases obtained from the curing were albite-calcite and crystallized particles such C-S-H similar to the autoclaved brick. Lime-brick stored at room temperature under moist condition for 28 days gave the equivalent value of strength to 6 h autoclaved brick. New phases were similar to those obtained from the autoclaved bricks. Hydrothermal process also increased the pozzolanic reactivity of lime-bottom ash bricks.



ลิขสิทธิ์มหาวิทยาลัยเชียงใหม่
Copyright© by Chiang Mai University
All rights reserved