4	4	9	9	6
ห ัล	156	งการก	61.J.9 (941 9	115
טע	890	1 1 1 1	บเหท	μп

ผู้เขียน

ปริญญา

อิทธิพลของสภาวะการเตรียมต่อการเติบโตของอนุภาคซิงค์ออก ไซด์ที่สังเกราะห์โดยวิธีไมโกรเวฟ-ไฮโดรเทอร์มอล นายณัฑพร มโนใจ วิทยาศาสตรมหาบัณฑิต (เกมี)

อาจารย์ที่ปรึกษาวิทยานิพนธ์

บทคัดย่อ

คร. นาวี กังวาลย์

ฟิล์มบางซิงก์ออกไซด์ถูกสังเคราะห์โดยวิธีไมโครเวฟไฮโครเทอร์มอลซึ่งถูกเตรียมบน แผ่นแก้วไอทีโอ (ITO)โดยวิธีจุ่ม วิธีสเปรย์ไพโรไลซิสที่อุณหภูมิ 80 องศาเซลเซียสและการให้ ความร้อนโดยการแผ่รังสีไมโครเวฟ ซิงก์ไนเตรตและเฮกซะเมทิลลีนเตตระมีนถูกใช้เป็น สารละลายตั้งค้นที่เตรียมในเวสเซลภายใต้สภาวะต่างๆ และทำการสังเคราะห์ที่อุณหภูมิ90 องศา เซลเซียสเป็นเวลา 4 ชั่วโมงและนำไปผ่านกระบวนการอบอ่อนที่อุณหภูมิ 400 องศาเซลเซียสเป็น เวลา 2 ชั่วโมงโครงสร้างและสัณฐานวิทยาของผลิตภัณฑ์ที่สังเคราะห์ได้ถูกนำไปหาลักษณะเฉพาะ โดยการเลี้ยวเบนของรังสีเอ็กซ์และกล้องจุลทรรศนศาสตร์อิเล็กตรอนแบบส่องกราค รูปแบบการ เลี้ยวเบนของรังสีเอ็กซ์สัมพันธ์กับโครงสร้างของซิงค์ออกไซก์ในแฟ้มข้อมูล JCPDS หมายเลข 80-74 ซึ่งยืนยันว่าซิงค์ออกไซด์ที่ได้มีโครงสร้างแบบเฮกซะโกนอล แท่งขนาดนาโนซิงก์ออกไซด์ มี สัณฐานวิทยาคล้ายกลุ่มของดอกไม้ที่สภาวะการเตรียมที่แตกต่างกัน วิธีสเปรย์ไพโรไลซิสที่ อัตราส่วนความเข้มข้นต่างๆ ขนาดของดอกเล็กกว่าและมีการแตกหักมากกว่าวิธีจุ่ม สำหรับการ เตรียมโดยการแผ่รังสีไมโครเวฟมีสัณฐานวิทยาคล้ายดอกไม้ที่สภาวะการเตรียมที่แตกต่างกันและ จากการวิเคราะห์โดยใช้ EDS เพื่อตรวจสอบธาตุชิงก์และออกซิเจนก็ยืนยันว่าเป็นซิงค์ออกไซด์

Copyright[©] by Chiang Mai University All rights reserved

Thesis Title	Influence of Preparative Conditions on Particle Growth of Zinc		
	Oxide Synthesized by Microwave-Hydrothermal Method		
Author	Mr. Natthaporn Manojai		
Degree	Master of Science (Chemistry)		
Thesis Advisor	Dr. Nawee Kungwan		

ABSTRACT

ZnO nanorods of thin film were synthesized by using the microwavehydrothermal method. Films were deposited on ITO glass substrates using the dipcoating method along with the spray pyrolysis method at 80°C and were heated by using microwave irradiation. A combination of zinc nitrate and hexamethylene tetramine was used as the precursor solution. The solution was taken in hydrothermal vessels under different conditions and synthesized at 90 °C for four hours. The ZnO thin film nanorods were obtained following an annealing process at 400 °C for two hours. The structure and morphology of the synthesized products were verified by Xray diffraction and scanning electron microscopy (SEM). The X-ray diffraction patterns showed that this diffraction pattern perfectly matches the crystal structure for ZnO (JCPD file No. 80-74) which confirms that the obtained ZnO possesses a hexagonal structure. The ZnO nanorod exhibits a flowerlike cluster in the precursor solution. During spray pyrolysis with a different ratio of precursor concentration, the flower cluster ZnO nanorods, having smaller sizes and morphology, are broken more than the dip-coating method. The seed ZnO prepared by using microwave irradiation exhibits the flowerlike cluster under the different condition. The EDS analysis of chemical elements Zn and O clearly confirmed the ZnO nanorods.